



# MAGNALUBE GREASE® MATERIAL DATA AND SAFETY SHEET

# MAGNALUBE® GREASE



## BENEFITS FOR THE CUSTOMER

### Material and labour costs

One application of Magnalube® Grease will do the same job as six applications of conventional grease – thus smaller grease inventory.

- **Equipment runs smoother and longer**  
Magnalube-G deposits a fine protective and lubricating film on metal that will continue to function even after grease has extruded away.
- **Downtime reduced**  
Maintenance downtime periods are reduced or eliminated through the efficiency of this lubricant. Also no mess or contamination.
- **Temperature/Load problem solver**  
Microparticles of TEFLON® suspended in Magnalube-G ensure continued performance of equipment operating at high loads and extreme temperatures.
- **Resistant to water and weather**  
Provides extended protection against rust in moist environments and won't migrate from hot surfaces - a real plus on precision equipment and heavy machinery.

Many other design advantages make Magnalube-G the finest multi-purpose lubricant. Not classified as hazardous with the criteria of worksafe Australia.

## UNLIMITED APPLICATIONS

Actuators | Brake calipers | Computers | Construction equipment | Railroad couplings | Die-casting machines | Electric switches | Gaskets | Gears, bearings & jack screws | Hydraulic & industrial equipment | Mould release | Motors | Office business machines | Pneumatic cylinders | Pumps | Railroad engines | Seals | Tools | Trucks & trailers | Valves

## PROVEN PERFORMANCE

**Magnalube-G** deposits a fine protective and lubricating film on metal parts. It is virtually unaffected by corrosive moisture and will not migrate from hot surfaces.

**Magnalube-G** is water resistant, stable at high temperatures, resists oil separation, and is chemically and mechanically stable. The **TEFLON®** base effectively lubricates at temperatures -40 °C to 288 °C. The applications are unlimited.

## TECHNICAL SPECIFICATIONS

- Low Temperature Torque® -37 °C (ASTMD – 1478)
- Starting Torque® – 740 N.m  
Running Torque® – 103.5 N.m
- **High Temperature Performance**  
500 hours – 10,000 RPM @ 232 °C – Pass  
Roll Stanility Test – 4 hours – No Change  
Oxidation Stability – 100 hrs, @210 °F, ASTM D 942 10 Max
- **Base oil**  
Viscosity at 40 °C: CS 193  
Viscosity at 100 °F: SSU 900  
Viscosity at 100 °C: CS 15.4  
Viscosity at 210 °F: SSU 79.8  
Pour Point at -12 °C  
Timken EP, 20.4 kg

## AVAILABLE SIZES

Article number	Type
R50612	Magnalube-G 25 KG DRUM
R50592	Magnalube-G 4 KG TIN
R50599	Magnalube-G 1 KG TIN
R50582	Magnalube-G 500 GM TIN
R50587	Magnalube-G 450 GM CARTRIDGE
R50614	Magnalube-G 250 GM JAR
R50586	Magnalube-G 250 GM TIN
R50581	Magnalube-G 100 GM JAR
R50567	Magnalube-G 21.25 GM TUBE
R50583	Magnalube-G 4 CC TUBE

## HAZARDS IDENTIFICATION

### First aid measures

Complaints	Remedy
Ingestion	<ul style="list-style-type: none"> <li>• Do not induce vomiting</li> <li>• Get medical attention immediately</li> <li>• Do not give milk or oil</li> <li>• Administer large amounts of water</li> <li>• If vomiting occurs, keep head low so that stomach content does not get into the lungs</li> </ul>
Eyes	<ul style="list-style-type: none"> <li>• Rinse the eye with water immediately</li> <li>• Continue to rinse for at least 15 minutes</li> <li>• Contact physician if discomfort continues</li> </ul>
Inhalation	<ul style="list-style-type: none"> <li>• Vapor inhalation is normally not a problem</li> <li>• If overcome by vapor of hot product, immediately remove exposed person from source of exposure</li> <li>• Move the exposed person to fresh air at once. For breathing difficulties oxygen may be necessary</li> <li>• Get medical attention if any discomfort continues</li> </ul>
Skin	<ul style="list-style-type: none"> <li>• Remove contaminated clothing</li> <li>• Wash skin thoroughly with soap and water</li> <li>• Get medical attention if any discomfort continues</li> </ul>

## HANDLING AND STORAGE

Precautions for safe handling	
Handling Precautions	Keep away from heat, sparks and open flame. Ventilate well, avoid breathing vapors. Use approved respirator if air contamination is above accepted level. Do not reuse container. Keep lid closed when not in use. Do not store or mix with strong oxidizers. Avoid spilling, skin and eye contact. Eye wash and emergency shower must be available at the work place
Handling Description	Prevent small spills and leakages to avoid slip hazard
Storage Precautions	Store separate from strong acids and oxidizers. Keep away from heat, sparks and open flame
Storage Criteria	Chemical storage

Editorial information  
Freudenberg FST GmbH  
Höhnerweg 2-4  
69465 Weinheim, Germany

Published by:  
Freudenberg Sealing Technologies Pty Ltd.  
42 Kremzow Rd, Brendale, QLD 4500  
Phone: 131 858  
sales.au@fst.com  
www.fst.com | australiashop.fst.com | dichtomatik.fst.com

July 2020

# CONTACT US

## YOUR LOCAL SUPPORT IN AUSTRALIA

### QUEENSLAND (HEAD OFFICE)

Phone: 131 858  
Email: sales.au@fst.com  
Address: 42 Kremzow Road, Brendale QLD 4500

### SOUTH AUSTRALIA

Phone: 131 858  
Email: sales.au@fst.com

### NEW SOUTH WALES

Phone: 131 858  
Email: sales.au@fst.com  
Address: Unit 11 / 14 Holbeche Road, Arndell Park NSW 2148

### WESTERN AUSTRALIA

Phone: 131 858  
Email: sales.au@fst.com  
Address: 57 Tacoma Circuit, Canning Vale WA 6155

### VICTORIA

Phone: 131 858  
Email: sales.au@fst.com  
Address: 3 Brand Drive, Thomastown VIC 3074

## LEGAL NOTICE

The information contained herein is considered to be reliable, but no assurances, warrants or guarantees whatsoever, of any kind, are provided with regard to their correctness or suitability for any purpose. The information reproduced herein is based on the current state of the technology and is not necessarily indicative of the performance of the end product. Complete testing and the performance of the end product are the user's responsibility.